



Pre- Stretch NoCo Wrap Technical Data Sheet

- No core to throw away
- Superior Load Holding Strength
- 100% recyclable & eco-friendly
- Various handle options available
- Available in various colors – Black, Blue, Green, Red, Orange, Yellow, Purple, White (Custom Colors are available up on request)
- Product Categories – GW, GWNW, ZGWHF

Thickness	ASTM D-4649	Mic	8.5 mic.
Tensile Ultimate MD	ASTM D-882	PSI	15000
Tensile Ultimate TD	ASTM D-882	PSI	3800
Tensile Yield MD	ASTM D-882	PSI	7250
Tensile Yield TD	ASTM D-882	PSI	1400
Elongation MD	ASTM D-882	%	180
Elongation TD	ASTM D-882	%	690
Elmendorf Tear MD	ASTM D-1922	g/mil	180
Elmendorf Tear TD	ASTM D-1922	g/mil	680
Cling	ASTM D-5458	g/in	150

Thickness	ASTM D-4649	Mic	7.4 mic.
Tensile Ultimate MD	ASTM D-882	PSI	15500
Tensile Ultimate TD	ASTM D-882	PSI	3500
Tensile Yield MD	ASTM D-882	PSI	6950
Tensile Yield TD	ASTM D-882	PSI	1250
Elongation MD	ASTM D-882	%	80
Elongation TD	ASTM D-882	%	690
Elmendorf Tear MD	ASTM D-1922	g/mil	180
Elmendorf Tear TD	ASTM D-1922	g/mil	680
Cling	ASTM D-5458	g/in	150

- ***All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.***

Email: info@wraptite.com, **B2B:** www.wraptite.com

Head Quarters: 6200 Cochran Road, Solon, Ohio 44139

Phone: 440-349-5400

Mfg Website: www.wraptitemanufacturing.com

Manufacturing: 6250 Camp Industrial Road, Solon, Ohio 44139

Fax: 440-349-5432