



"Your Source For Packaging, Shipping & Safety Supplies"
"Ship right with Wrap-Tite"



Narrow Width Hand Film Technical Data Sheet

- Quite Unwinding Stiff & Strong Cast Film
- Superior Load Holding Strength
- Self-Clinging without residue
- Low cost alternative to tape, twine, and strapping
- Available in various colors (Dark & Tinted) – Black, Blue, Green, Red, Orange, Yellow, Purple, White (Custom Colors are available up on request)
- Product Categories – CNW, CEX, CBR (For Orbital wrappers), CPW, CCU, ZNW, ZPW, All Printed Narrow Widths



Thickness	ASTM D-4649	Gauge	60 ga	65 ga	70 ga	75 ga	80 ga	90 ga	100 ga	115 ga	120 ga	135 ga	150 ga
Tensile Ultimate MD	ASTM D-882	PSI	6400	6400	6450	6450	6500	6500	6600	6600	6600	6600	6600
Tensile Ultimate TD	ASTM D-882	PSI	4000	4000	4050	4050	4100	4100	4150	4150	4150	4150	4150
Tensile Yield MD	ASTM D-882	PSI	1250	1250	1275	1275	1300	1300	1350	1350	1350	1350	1350
Tensile Yield TD	ASTM D-882	PSI	1200	1200	1200	1200	1200	1200	1200	1200	1200	1200	1200
Elongation MD	ASTM D-882	%	390	390	360	360	330	330	310	310	310	310	310
Elongation TD	ASTM D-882	%	610	610	570	570	540	540	520	520	520	520	520
Elmendorf Tear MD	ASTM D-1922	g/mil	350	350	340	340	330	330	310	310	310	310	310
Elmendorf Tear TD	ASTM D-1922	g/mil	600	600	570	570	540	540	520	520	520	520	520
Cling@100%	ASTM D-5458	g/in	180	180	180	180	180	180	180	180	180	180	180

All values are representative of typical film performance and are not to be construed as manufacturing and/or sales specifications.

Email: info@wraptite.com, B2B: www.wraptite.com

Head Quarters: 6200 Cochran Road, Solon, Ohio 44139

Phone: 440-349-5400

Mfg Website: www.wraptite.com/manufacturing/

Manufacturing: 6075 Cochran Road, Solon, Ohio 44139

Fax: 440-349-5432